


## Rotec Bridas ciegas

Resina Epoxi (GRE)

Drilling Standard: AS 2129 Table D



#	DN (mm)	Pmax (bar)	D (mm)	k (mm)	Holes (no.)	d2 (mm)	T (mm)	Article Number
1	150	10	285	235	8	18	22	BFE-150-10/AS-D
2	150	16	285	235	8	18	28	BFE-150-16/AS-D
3	200	10	350	292	8	18	25	BFE-200-10/AS-D
4	200	16	350	292	8	18	35	BFE-200-16/AS-D
5	250	10	410	356	8	22	35	BFE-250-10/AS-D
6	250	16	410	356	8	22	40	BFE-250-16/AS-D
7	300	10	460	406	12	22	40	BFE-300-10/AS-D
8	300	16	460	406	12	22	48	BFE-300-16/AS-D
9	350	10	540	470	12	26	44	BFE-350-10/AS-D
10	350	16	540	470	12	26	52	BFE-350-16/AS-D
11	400	10	600	521	12	26	48	BFE-400-10/AS-D
12	400	16	600	521	12	26	60	BFE-400-16/AS-D
13	450	10	644	584	12	26	52	BFE-450-10/AS-D
14	450	16	644	584	12	26	68	BFE-450-16/AS-D
15	500	3	720	641	16	26	35	BFE-500-03/AS-D
16	500	6	720	641	16	26	44	BFE-500-06/AS-D


### Disclaimer

Whilst every care is taken to ensure that the information on this website is complete and accurate, the Rotec Composite Group BV cannot accept responsibility for any omissions or inaccuracies or for any consequences arising therefrom. By using this website, the user accepts the terms of this disclaimer.

## Rotec Bridas ciegas

### Resina Epoxi (GRE)

Drilling Standard: AS 2129 Table D



#	DN (mm)	Pmax (bar)	D (mm)	k (mm)	Holes (no.)	d2 (mm)	T (mm)	Article Number
17	500	10	720	641	16	26	60	BFE-500-10/AS-D
18	500	16	720	641	16	26	74	BFE-500-16/AS-D
19	550	3	775	699	16	30	40	BFE-550-03/AS-D
20	550	6	775	699	16	30	52	BFE-550-06/AS-D
21	550	10	775	699	16	30	64	BFE-550-10/AS-D
22	550	16	775	699	16	30	80	BFE-550-16/AS-D
23	600	3	844	756	16	30	44	BFE-600-03/AS-D
24	600	6	844	756	16	30	52	BFE-600-06/AS-D
25	600	10	844	756	16	30	68	BFE-600-10/AS-D
26	600	16	844	756	16	30	85	BFE-600-16/AS-D
27	700	3	910	845	20	30	48	BFE-700-03/AS-D
28	700	6	910	845	20	30	60	BFE-700-06/AS-D
29	700	10	910	845	20	30	74	BFE-700-10/AS-D
30	700	16	910	845	20	30	92	BFE-700-16/AS-D
31	800	3	1085	984	20	36	60	BFE-800-03/AS-D
32	800	6	1085	984	20	36	68	BFE-800-06/AS-D
33	800	10	1085	984	20	36	85	BFE-800-10/AS-D

#### Disclaimer

Whilst every care is taken to ensure that the information on this website is complete and accurate, the Rotec Composite Group BV cannot accept responsibility for any omissions or inaccuracies or for any consequences arising therefrom. By using this website, the user accepts the terms of this disclaimer.

## Rotec Bridas ciegas

### Resina Epoxi (GRE)

Drilling Standard: AS 2129 Table D



#	DN (mm)	Pmax (bar)	D (mm)	k (mm)	Holes (no.)	d2 (mm)	T (mm)	Article Number
34	800	16	1085	984	20	36	105	BFE-800-16/AS-D
35	900	3	1190	1092	24	36	60	BFE-900-03/AS-D
36	900	6	1190	1092	24	36	78	BFE-900-06/AS-D
37	900	10	1190	1092	24	36	95	BFE-900-10/AS-D
38	900	16	1190	1092	24	36	115	BFE-900-16/AS-D
39	1000	3	1265	1175	24	36	68	BFE-1000-03/AS-D
40	1000	6	1265	1175	24	36	85	BFE-1000-06/AS-D
41	1000	10	1265	1175	24	36	105	BFE-1000-10/AS-D
42	1000	16	1265	1175	24	36	130	BFE-1000-16/AS-D
43	1200	3	1540	1410	32	36	80	BFE-1200-03/AS-D
44	1200	6	1540	1410	32	36	105	BFE-1200-06/AS-D
45	1200	10	1540	1410	32	36	120	BFE-1200-10/AS-D
46	1200	16	1540	1410	32	36	155	BFE-1200-16/AS-D
47	1400	3	1700	1615	36	36	95	BFE-1400-03/AS-D
48	1400	6	1700	1615	36	36	120	BFE-1400-06/AS-D
49	1400	10	1700	1615	36	36	140	BFE-1400-10/AS-D
50	1400	16	1700	1615	36	36	175	BFE-1400-16/AS-D

#### Disclaimer

Whilst every care is taken to ensure that the information on this website is complete and accurate, the Rotec Composite Group BV cannot accept responsibility for any omissions or inaccuracies or for any consequences arising therefrom. By using this website, the user accepts the terms of this disclaimer.

## Rotec Bridas ciegas

### Resina Epoxi (GRE)

Drilling Standard: AS 2129 Table D



#	DN (mm)	Pmax (bar)	D (mm)	k (mm)	Holes (no.)	d2 (mm)	T (mm)	Article Number
51	1600	3	1950	1825	40	39	100	BFE-1600-03/AS-D
52	1600	6	1950	1825	40	39	130	BFE-1600-06/AS-D
53	1600	10	1950	1825	40	39	155	BFE-1600-10/AS-D
54	1600	16	1950	1825	40	39	200	BFE-1600-16/AS-D
55	1800	3	2150	2019	44	42	120	BFE-1800-03/AS-D
56	1800	6	2150	2019	44	42	145	BFE-1800-06/AS-D
57	1800	10	2150	2019	44	42	175	BFE-1800-10/AS-D
58	1800	16	2150	2019	44	42	225	BFE-1800-16/AS-D
59	2000	3	2360	2250	44	42	125	BFE-2000-03/AS-D
60	2000	6	2360	2250	44	42	160	BFE-2000-06/AS-D
61	2000	10	2360	2250	44	42	195	BFE-2000-10/AS-D
62	2200	3	2580	2460	44	48	135	BFE-2200-03/AS-D
63	2200	6	2580	2460	44	48	175	BFE-2200-06/AS-D
64	2200	10	2580	2460	44	48	210	BFE-2200-10/AS-D
65	2400	3	2810	2673	52	48	155	BFE-2400-03/AS-D
66	2400	6	2810	2673	52	48	200	BFE-2400-06/AS-D
67	2400	10	2810	2673	52	48	240	BFE-2400-10/AS-D

#### Disclaimer

Whilst every care is taken to ensure that the information on this website is complete and accurate, the Rotec Composite Group BV cannot accept responsibility for any omissions or inaccuracies or for any consequences arising therefrom. By using this website, the user accepts the terms of this disclaimer.